

VICTREX® PEEK™ 450FC30

➤ **Product Description:**

High performance thermoplastic material, 30% reinforced with carbon fibre / graphite / PTFE PolyEtherEtherKetone (PEEK), semi crystalline, granules for injection moulding and extrusion, standard flow, colour black.

➤ **Typical Application Areas:**

Tribological applications for high strength. Excellent wear resistance, very low coefficient of friction, low coefficient of thermal expansion. Chemically resistant to aggressive environments.

➤ **Material Properties**

	CONDITIONS	TEST METHOD	UNITS	TYPICAL VALUE
Mechanical Data				
Tensile Strength	Break, 23°C	ISO 527	MPa	140
	Break, 125°C			95
	Break, 175°C			55
	Break, 225°C			45
	Break, 275°C			35
Tensile Elongation	Break, 23°C	ISO 527	%	2.2
Tensile Modulus	23°C	ISO 527	GPa	12.5
Flexural Strength	23°C	ISO 178	MPa	230
Flexural Modulus	23°C	ISO 178	GPa	11.5
Compressive Strength	23°C	ISO 604	MPa	170
	120°C			110
Charpy Impact Strength	Notched, 23°C	ISO 179/1eA	kJ m ⁻²	5.0
	Unnotched, 23°C	ISO 179/1U	kJ m ⁻²	35
Izod Impact Strength	Notched, 23°C	ISO 180/A	kJ m ⁻²	6.0
	Unnotched, 23°C	ISO 180/U		35
Thermal Data				
Melting Point		ISO 3146	°C	343
Glass Transition (Tg)		ISO 3146	°C	143
Specific Heat Capacity	23°C	DSC	kJ kg ⁻¹ °C ⁻¹	1.8
Coefficient of Thermal Expansion	Along flow below Tg	ISO 11359	ppm °C ⁻¹	15
	Average below Tg			45
	Along flow above Tg			20
	Average above Tg			115
Heat Deflection Temperature	1.8 MPa	ISO 75-f	°C	315
Thermal Conductivity	23°C	ISO/CD 22007-4	W m ⁻¹ °C ⁻¹	0.87
Continuous Use Temperature	Mechanical w/o impact	UL 746B	°C	240
	Mechanical w/impact			180
Flow				
Melt Viscosity	400°C	ISO 11443	Pa.s	550

Miscellaneous				
Density	Crystalline	ISO 1183	g cm ⁻³	1.45
Shore D hardness	23 °C	ISO 868		85
Water Absorption (3.2mm thick Tensile bar)	24 h, 23 °C	ISO 62-1	%	0.04
(by immersion)	Equilibrium, 23 °C			0.3

Fire Smoke Toxicity				
Flammability Rating		UL94	n/a	V-0 @ 0.75 mm
Glow Wire Test	2mm thickness	IEC 60695-2-12	°C	960
Limiting Oxygen Index		ISO 4289	%O ₂	43

Recommended Processing Conditions	
Drying Temperature / Time	150 °C / 3h or 120 °C / 5h
Temperature settings	360 / 365 / 375 / 380 °C (Nozzle)
Hopper Temperature	Not greater than 100 °C
Mould Temperature	170 °C - 200 °C (max 250 °C)
Mould Shrinkage	Along Flow, 3 mm, 170 °C mould, 0.3% Across flow, 3 mm, 170 °C mould, 0.5%
Runner	Die / nozzle >3mm, manifold >3.5mm
Gate	>2mm or 0.5 x part thickness

Detailed data available on our website www.victrex.com or upon request



World Headquarters

Victrex plc, Hillhouse International, Thornton Cleveleys, Lancashire FY5 4QD United Kingdom
 Tel: + (44) 1253 897700 Fax: + (44) 1253 897701 Email: victrexplc@victrex.com

VICTREX PLC BELIEVES THAT THE INFORMATION CONTAINED IN THIS BROCHURE IS AN ACCURATE DESCRIPTION OF THE TYPICAL CHARACTERISTICS AND/OR USES OF THE PRODUCT OR PRODUCTS, BUT IT IS THE CUSTOMER'S RESPONSIBILITY TO THOROUGHLY TEST THE PRODUCT IN EACH SPECIFIC APPLICATION TO DETERMINE ITS PERFORMANCE, EFFICACY AND SAFETY FOR EACH END-USE PRODUCT, DEVICE OR OTHER APPLICATION. SUGGESTIONS OF USES SHOULD NOT BE TAKEN AS INDUCEMENTS TO INFRINGE ANY PARTICULAR PATENT. THE INFORMATION AND DATA CONTAINED HEREIN ARE BASED ON INFORMATION WE BELIEVE RELIABLE. MENTION OF A PRODUCT IN THIS DOCUMENTATION IS NOT A GUARANTEE OF AVAILABILITY. VICTREX PLC RESERVES THE RIGHT TO MODIFY PRODUCTS, SPECIFICATIONS AND/OR PACKAGING AS PART OF A CONTINUOUS PROGRAM OF PRODUCT DEVELOPMENT. VICTREX® IS A REGISTERED TRADEMARK OF VICTREX MANUFACTURING LIMITED. VICOTE® IS A REGISTERED TRADEMARK OF VICTREX PLC. PEEK™, APTIV™ AND PEEK-HT™ ARE TRADEMARKS OF VICTREX PLC.

VICTREX PLC MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, A WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR OF INTELLECTUAL PROPERTY NON-INFRINGEMENT, INCLUDING, BUT NOT LIMITED TO PATENT NON-INFRINGEMENT, WHICH ARE EXPRESSLY DISCLAIMED, WHETHER EXPRESS OR IMPLIED, IN FACT OR BY LAW. FURTHER, VICTREX PLC MAKES NO WARRANTY TO YOUR CUSTOMERS OR AGENTS, AND HAS NOT AUTHORIZED ANYONE TO MAKE ANY REPRESENTATION OR WARRANTY OTHER THAN AS PROVIDED ABOVE. VICTREX PLC SHALL IN NO EVENT BE LIABLE FOR ANY GENERAL, INDIRECT, SPECIAL, CONSEQUENTIAL, PUNITIVE, INCIDENTAL OR SIMILAR DAMAGES, INCLUDING WITHOUT LIMITATION, DAMAGES FOR HARM TO BUSINESS, LOST PROFITS OR LOST SAVINGS, EVEN IF VICTREX HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES, REGARDLESS OF THE FORM OF ACTION.

